

# Lionpak<sup>®</sup>

## 2501

PTFE/aramid for abrasion resistance with low friction

**Lionpak<sup>®</sup> 2501 is a dense braided combination packing, with tough aramid yarn at the corners, PTFE yarn at the faces, and a strong core of extruded and expanded PTFE cord.**

The aramid yarn is impregnated with an anti-friction fluoropolymer dispersion and a break-in lubricant, while the PTFE faces are treated with a high temperature resistant and inert lubricant.

Note that the expanded PTFE core is supplied in packings of cross section 6.5mm (or 1/4") and greater; sections less than these dimensions are braided over a core of PTFE yarn.

### Prime features

- Dense construction that offers excellent sealability.
- Aramid corners enhance long life in harsh plunger pump applications.
- Expanded PTFE core provides improved compressibility and responsiveness, compared to the aramid core typically used on similar products.
- PTFE faces provide low friction and low-wear running on shafts.

### Typical applications

Centrifugal, reciprocating and plunger pumps (particularly dosing pumps), valves, reactors, autoclaves and agitators. It can also be used as a replacement for traditional lip seals in certain applications.

Suitable for use with ammonia, urea and carbamate condensate in fertiliser plant, pigments, dyestuffs, paints, amide, detergents, hydrazine, trisodium phosphate, sodium hexametaphosphate and slurries.

### Chemical properties

Compatible with media in the range pH 1-13.

### How supplied

All popular square sections from 4 mm to 50 mm (<sup>5</sup>/<sub>32</sub>" to 2") in boxes containing 8 m (26' 3"), or in coil form by the metre/foot or kilogram/pound. Also supplied as split preformed rings and sets.



### SPECIALISED PACKING



#### VALVE STEM DUTIES

**Maximum Operating Temperature:**

+250°C (+482°F)

**Minimum Temperature:**

-50°C (-58°F)

**Maximum System Pressure:**

25 MPa/250 bar (3626 psi)



#### CENTRIFUGAL PUMPS AND ROTARY EQUIPMENT

**Maximum Operating Temperature:**

+250°C (+482°F)

**Minimum Operating Temperature:**

-50°C (-58°F)

**Maximum Shaft Speed:**

20 m/s (3937 fpm)

**Maximum System Pressure:**

2 MPa/20 bar (290 psi)



#### RECIPROCATING PUMPS AND RAMS

**Maximum Operating Temperature:**

+250°C (+482°F)

**Minimum Operating Temperature:**

-50°C (-58°F)

**Maximum Rod Speed:**

2.0 m/s (394 fpm)

**Maximum System Pressure:**

10 MPa/100 bar (1450 psi)

# James Walker Distributor

## **Sweden and Denmark**

### **G A Lindberg Sealtech AB**

**Raseborgsgatan 9  
164 06 Kista  
Sweden**

**T: +46 (0)8 703 02 00**

**E: [sealinfo@galindberg.se](mailto:sealinfo@galindberg.se)**

**Health warning:** If PTFE products are heated to elevated temperatures, fumes will be produced which may give unpleasant effects, if inhaled. Whilst some fumes are emitted below 300°C (572°F) from PTFE, the effect at these temperatures is negligible. Care should be taken to avoid contaminating tobacco with particles of PTFE or PTFE dispersion, which may remain on hands or clothing. Safety Data Sheets (SDS) are available on request.

Information given in this publication is given in good faith and represents the results of specific individual tests carried out by James Walker or third parties in accordance with the methodologies described in this publication, performed in a laboratory. No representation or warranty is given in relation to such information. Values and/or operating limits given in this publication are not an indication that these values and/or operating limits can be applied simultaneously. While such results may comprise useful additional information and are industry standard tests, they are no substitute for conducting (or procuring from James Walker) your own tests and engineering analysis and satisfying yourself as to the suitability of the product you select. Please also note that a product tested in accordance with the published methodology may not perform to such values in application and/or under different test conditions or methodologies for a variety of reasons, including but not limited to the environment in which it is used/tested or which passes through it or otherwise affects the product, or due to the handling, storage or installation, or due to the effect of housing or other parts. Our personnel will be happy to discuss any historical examples we have of a product having been previously used in a particular application.

To ensure you are working with the very latest product specifications, please consult the relevant section of the James Walker website: [www.jameswalker.biz](http://www.jameswalker.biz).

Names bearing the ® symbol are registered trademarks of James Walker Group or associated companies

#### **James Walker Sealing Products & Services Ltd**

Registered Office: Lion House, Oriental Road,  
Woking, Surrey GU22 8AP, United Kingdom.

Reg no: 00264191 England

# Quick reference chart

Product	Valve	Rotary		Reciprocating		Static
	Pressure MPa (psi)	Shaft Speed m/s (fpm)	Pressure MPa (psi)	Rod Speed m/s (fpm)	Pressure MPa (psi)	Pressure MPa (psi)
<b>PTFE-based</b>						
Lionpak® 2100	25 (3626)	4 (787)	1 (145)	0.5 (98)	5 (725)	n/a
Lionpak® 2101	25 (3626)	4 (787)	1 (145)	0.5 (98)	5 (725)	n/a
Lionpak® 2102	25 (3626)	5 (984)	2 (290)	0.5 (98)	15 (2175)	n/a
Lionpak® 2200	15 (2175)	10 (1969)	2.5 (363)	1 (197)	10 (1450)	n/a
Lionpak® 2201	15 (2175)	10 (1969)	2.5 (363)	1 (197)	10 (1450)	n/a
Lionpak® 2202	15 (2175)	12 (2362)	2.5 (363)	1 (197)	15 (2175)	n/a
Lionpak® 2300	8 (1160)	22 (4331)	1 (145)	1 (197)	8 (1160)	n/a
Lionpak® 2302	8 (1160)	22 (4331)	1 (145)	1 (197)	8 (1160)	n/a
Lionpak® 2303	12 (1740)	17.5 (3445)	2 (290)	2 (394)	8 (1160)	n/a
Lionpak® 2500	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2501	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2502	25 (3626)	20 (3937)	2 (290)	2 (394)	20 (2900) <sup>‡</sup>	n/a
Lionpak® 2503	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2504	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2505	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 2506	25 (3626)	22 (4331)	2 (290)	2 (394)	10 (1450)	n/a
<b>Aramid-based</b>						
Lionpak® 3200	15 (2175)	20 (3937)	2.5 (363)	1.5 (295)	15 (2175)	n/a
Lionpak® 3301	15 (2175)	20 (3937)	2.5 (363)	1.5 (295)	15 (2175)	n/a
Lionpak® 3302	15 (2175)	20 (3937)	2.5 (363)	1.5 (295)	10 (1450)	n/a
<b>Graphite/Carbon-based</b>						
Lionpak® 5100	25 (3626)	25 (4921)	2.5 (363)	n/a	n/a	n/a
Lionpak® 5101	10 (1450)	20 (3937)	3.5 (508)	n/a	n/a	n/a
Lionpak® 5200	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5201	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5202	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5300	15 (2175)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5301	20 (2900)	20 (3937)	2 (290)	2 (394)	15 (2175) <sup>‡</sup>	n/a
Lionpak® 5302	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 5303	20 (2900)	20 (3937)	2 (290)	2 (394)	15 (2175) <sup>‡</sup>	n/a
Lionpak® 5304	20 (2900)	20 (3937)	2 (290)	2 (394)	15 (2175) <sup>‡</sup>	n/a
Lionpak® 5501	25 (3626)	Consult	Consult	n/a	n/a	n/a
Lionpak® 5503	25 (3626)	Consult	Consult	n/a	n/a	n/a
Lionpak® 5504	25 (3626)	Consult	Consult	n/a	n/a	n/a
Lionpak® 5505	25 (3626)	n/a	n/a	n/a	n/a	n/a

Key	
1	+450°C (+930°F) oxidising conditions, +550°C (+1202°F) steam, +850°C (+1562°F) non-oxidising
2	+450°C (+842°F) oxidising conditions, +550°C (+1022°F) steam
3	+500°C (+930°F) oxidising conditions, +650°C (+1202°F) steam, +1000°C (+1832°F) non-oxidising
4	+1000°C (+1832°F) constant, +1100°C (+2012°F) intermittent
5	+450°C (+930°F) oxidising conditions, +650°C (+1202°F) steam, +1000°C (+1832°F) non-oxidising

Temperatures		pH	Media									
Min °C (°F)	Max °C (°F)	pH Range	Steam	Gases	Process Water	Potable Water	Strong Acids	Caustic Alkalis	Oils	Solvents	Oxygen	Food
<b>PTFE-based</b>												
-100 (-148)	+250 (+482)	0-14	✓	✓	✓	✓	✓	✓	✓	✓	X	X
-100 (-148)	+250 (+482)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+280 (+536)	0-14	✓	✓	✓	✓	✓	✓	✓	✓	X	✓
-100 (-148)	+250 (+482)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+250 (+482)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+280 (+536)	0-14	X	✓	✓	✓	✓	✓	✓	✓	X	✓
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	✓	✓	✓	✓	✓	X	X
-100 (-148)	+250 (+482)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+260 (+500)	2-13	✓	✓	✓	✓	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-100 (-148)	+250 (+482)	3-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+260 (+500)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
<b>Aramid-based</b>												
-50 (-58)	+250 (+482)	2-13	✓	✓	✓	✓	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-50 (-58)	+285 (+545)	0-13	✓	✓	✓	X	X	X	✓	✓	X	X
<b>Graphite/Carbon-based</b>												
-200 (-328)	+450 (+842) <sup>1</sup>	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842) <sup>2</sup>	1-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842) <sup>5</sup>	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842) <sup>2</sup>	1-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842) <sup>2</sup>	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+550 (+1022)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+450 (+842)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+450 (+842)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+350 (+662)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+500 (+932) <sup>3</sup>	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+500 (+932) <sup>3</sup>	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+500 (+932) <sup>3</sup>	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+350 (+662)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X

Key	
‡	May be suitable for higher pressures on certain reciprocating duties: please consult James Walker
Consult	Dependent on application; consult James Walker
n/a	Not applicable
✓	Suitable for application
X	Not suitable for application

Operating limits quoted in this publication are not an indication that these values can be applied simultaneously, particularly when operating near to the extreme limits. Please contact James Walker if you need further guidance on the suitability of any product for your specific application.

This brochure is supported by further detailed product data sheets and product fitting instructions which are available to download from the James Walker website at [www.jameswalker.biz](http://www.jameswalker.biz)