Lionpak®
2503

PTFE/graphite/aramid for highly abrasive chemical media

Lionpak® 2503 is a combination packing, with tough but smooth aramid fibre yarn at the corners, ePTFE/graphite solid yarn with a break-in lubricant at the faces, and a solid core of extruded elastomeric cord.

The aramid yarn is impregnated with an antifriction fluoropolymer dispersion and a special break-in lubricant.

Note that the extruded elastomeric core is supplied in packings of cross sections 6.5mm (or ¼") and greater; sections less than these dimensions are braided over a core of ePTFE/graphite yarn.

Prime features

- Exceedingly durable packing, with inherent dimensional stability, that offers high integrity sealing throughout its long operational life.
- PTFE/graphite running faces provide excellent heat dissipation with cool running.
- Aramid yarn at its corners helps to withstand the rigours of reciprocating plunger pump operation.
- For sections of 6mm (or ¼") and greater, the high density elastomeric core provides resilience and resistance to high working pressures, and can absorb the vibration and eccentric movement created by worn running surfaces.

Typical applications

Pumps, valves, reactors, autoclaves, mixers, agitators, refiners, pistons, hydraulic presses and hammers. It can also be used as a replacement for traditional lip seals in certain applications.

Recommended for duties with ammonia and carbamate solutions. Also suitable for use with oxidising and non-oxidising liquids and gases, fine chemical slurries, hydrazine, trisodium phosphate, sodium hexametaphosphate, black and green liquor, paper pulp, pulp diluted with water, water slurries, acids, alkalis and molasses.

Chemical properties

Compatible with media in the range pH 1-13.

How supplied

All popular square sections from 4mm to 50mm (5/32" to 2") in boxes containing 8m (26' 3"), or in coil form by the metre/foot or kilogram/pound. Also supplied as split preformed rings and sets.

VALVE STEM DUTIES

Maximum Operating Temperature:
+250°C (+482°F)

Minimum Operating Temperature:
-50°C (-58°F)

Maximum System Pressure:
25MPa/250bar (3626psi)

CENTRIFUGAL PUMPS AND ROTARY EQUIPMENT

Maximum Operating Temperature:
+250°C (+482°F)

Minimum Operating Temperature:
-50°C (-58°F)

Maximum Shaft Speed:
20m/s (3937fpm)

Maximum System Pressure:
2MPa/20bar (290psi)

RECIPROCATING PUMPS AND RAMS

Maximum Operating Temperature:
+250°C (+482°F)

Minimum Operating Temperature:
-50°C (-58°F)

Maximum Rod Speed:
2.0m/s (394fpm)

Maximum System Pressure:
10MPa/100bar (1450psi)

James Walker®

Ingeniörsfirman G A LINDBERG
DISTRIBUTOR IN SWEDEN AND DENMARK

James Walker Distributor

Sweden and Denmark

G A Lindberg Sealtech AB

Raseborgsgatan 9
164 06 Kista
Sweden

T: +46 (0)8 703 02 00
E: sealinfo@galindberg.se

Health warning: If PTFE products are heated to elevated temperatures, fumes will be produced which may give unpleasant effects, if inhaled. Whilst some fumes are emitted below 300°C (572°F) from PTFE, the effect at these temperatures is negligible. Care should be taken to avoid contaminating tobacco with particles of PTFE or PTFE dispersion, which may remain on hands or clothing. Safety Data Sheets (SDS) are available on request.

To ensure you are working with the very latest product specifications, please consult the relevant section of the James Walker website: **www.jameswalker.biz**.

James Walker Sealing Products & Services Ltd

Registered Office: Lion House, Oriental Road,
Woking, Surrey GU22 8AP, United Kingdom.

Reg no: 00264191 England

James Walker

Ingeniörsfirman G A LINDBERG
DISTRIBUTOR IN SWEDEN AND DENMARK

Quick reference chart

Product	Valve	Rotary		Reciprocating		Static
	Pressure MPa (psi)	Shaft Speed m/s (fpm)	Pressure MPa (psi)	Rod Speed m/s (fpm)	Pressure MPa (psi)	Pressure MPa (psi)
PTFE-based						
Lionpak® 2100	25 (3626)	4 (787)	1 (145)	0.5 (98)	5 (725)	n/a
Lionpak® 2101	25 (3626)	4 (787)	1 (145)	0.5 (98)	5 (725)	n/a
Lionpak® 2102	25 (3626)	5 (984)	2 (290)	0.5 (98)	15 (2175)	n/a
Lionpak® 2200	15 (2175)	10 (1969)	2.5 (363)	1 (197)	10 (1450)	n/a
Lionpak® 2201	15 (2175)	10 (1969)	2.5 (363)	1 (197)	10 (1450)	n/a
Lionpak® 2202	15 (2175)	12 (2362)	2.5 (363)	1 (197)	15 (2175)	n/a
Lionpak® 2300	8 (1160)	22 (4331)	1 (145)	1 (197)	8 (1160)	n/a
Lionpak® 2302	8 (1160)	22 (4331)	1 (145)	1 (197)	8 (1160)	n/a
Lionpak® 2303	12 (1740)	17.5 (3445)	2 (290)	2 (394)	8 (1160)	n/a
Lionpak® 2500	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2501	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2502	25 (3626)	20 (3937)	2 (290)	2 (394)	20 (2900)‡	n/a
Lionpak® 2503	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2504	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 2505	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 2506	25 (3626)	22 (4331)	2 (290)	2 (394)	10 (1450)	n/a
Aramid-based						
Lionpak® 3200	15 (2175)	20 (3937)	2.5 (363)	1.5 (295)	15 (2175)	n/a
Lionpak® 3301	15 (2175)	20 (3937)	2.5 (363)	1.5 (295)	15 (2175)	n/a
Lionpak® 3302	15 (2175)	20 (3937)	2.5 (363)	1.5 (295)	10 (1450)	n/a
Graphite/Carbon-based						
Lionpak® 5100	25 (3626)	25 (4921)	2.5 (363)	n/a	n/a	n/a
Lionpak® 5101	10 (1450)	20 (3937)	3.5 (508)	n/a	n/a	n/a
Lionpak® 5200	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5201	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5202	30 (4351)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5300	15 (2175)	n/a	n/a	n/a	n/a	n/a
Lionpak® 5301	20 (2900)	20 (3937)	2 (290)	2 (394)	15 (2175)‡	n/a
Lionpak® 5302	25 (3626)	20 (3937)	2 (290)	2 (394)	10 (1450)	n/a
Lionpak® 5303	20 (2900)	20 (3937)	2 (290)	2 (394)	15 (2175)‡	n/a
Lionpak® 5304	20 (2900)	20 (3937)	2 (290)	2 (394)	15 (2175)‡	n/a
Lionpak® 5501	25 (3626)	Consult	Consult	n/a	n/a	n/a
Lionpak® 5503	25 (3626)	Consult	Consult	n/a	n/a	n/a
Lionpak® 5504	25 (3626)	Consult	Consult	n/a	n/a	n/a
Lionpak® 5505	25 (3626)	n/a	n/a	n/a	n/a	n/a

Temperatures		pH	Media									
Min °C (°F)	Max °C (°F)	pH Range	Steam	Gases	Process Water	Potable Water	Strong Acids	Caustic Alkalis	Oils	Solvents	Oxygen	Food
PTFE-based												
-100 (-148)	+250 (+482)	0-14	✓	✓	✓	✓	✓	✓	✓	✓	X	X
-100 (-148)	+250 (+482)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+280 (+536)	0-14	✓	✓	✓	✓	✓	✓	✓	✓	X	✓
-100 (-148)	+250 (+482)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+250 (+482)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+280 (+536)	0-14	X	✓	✓	✓	✓	✓	✓	✓	X	✓
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	✓	✓	✓	✓	✓	X	X
-100 (-148)	+250 (+482)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+260 (+500)	2-13	✓	✓	✓	✓	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-100 (-148)	+250 (+482)	3-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+260 (+500)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+260 (+500)	0-14	X	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
Aramid-based												
-50 (-58)	+250 (+482)	2-13	✓	✓	✓	✓	X	X	✓	✓	X	X
-50 (-58)	+250 (+482)	1-13	✓	✓	✓	X	X	X	✓	✓	X	X
-50 (-58)	+285 (+545)	0-13	✓	✓	✓	X	X	X	✓	✓	X	X
Graphite/Carbon-based												
-200 (-328)	+450 (+842)[1]	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842)[2]	1-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842)[5]	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842)[2]	1-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+450 (+842)[2]	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+550 (+1022)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+450 (+842)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+450 (+842)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-50 (-58)	+350 (+662)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-100 (-148)	+260 (+500)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+500 (+932)[3]	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+500 (+932)[3]	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+500 (+932)[3]	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X
-200 (-328)	+350 (+662)	0-14	✓	✓	✓	X	✓	✓	✓	✓	X	X

Key	
1	+450°C (+930°F) oxidising conditions, +550°C (+1202°F) steam, +850°C (+1562°F) non-oxidising
2	+450°C (+842°F) oxidising conditions, +550°C (+1022°F) steam
3	+500°C (+930°F) oxidising conditions, +650°C (+1202°F) steam, +1000°C (+1832°F) non-oxidising
4	+1000°C (+1832°F) constant, +1100°C (+2012°F) intermittent
5	+450°C (+930°F) oxidising conditions, +650°C (+1202°F) steam, +1000°C (+1832°F) non-oxidising

Key	
‡	May be suitable for higher pressures on certain reciprocating duties: please consult James Walker
Consult	Dependent on application; consult James Walker
n/a	Not applicable
✓	Suitable for application
X	Not suitable for application

Operating limits quoted in this publication are not an indication that these values can be applied simultaneously, particularly when operating near to the extreme limits. Please contact James Walker if you need further guidance on the suitability of any product for your specific application.

This brochure is supported by further detailed product data sheets and product fitting instructions which are available to download from the James Walker website at www.jameswalker.biz